



The Toughest Hose Protection Products on the Planet...Period!

🥦 Rhino Blue Vinyl Wrap™



SRM Part #	Wrap I.D. (inches)	Wrap I.D. (mm)	Flat Width (inches)	Flat Width (mm)
RW-2.00-BLV	2.00″	50.80	7.75″	196
RW-3.00-BLV	3.00″	76.20	11.00″	279
RW-4.00-BLV	4.00″	101.60	14.00″	355
RW-5.00-BLV	5.00″	127.00	17.25″	438
RW-6.00-BLV	6.00″	152.40	20.38″	517
RW-7.00-BLV	7.00″	177.80	23.58″	598
RW-8.00-BLV	8.00″	203.20	26.62″	676

* Other Sizes available – minimum 1 – 150 foot roll required Contact us for pricing

Manufactured in the USA for SRM Industries Inc.

MATERIAL

- 35 oz. Vinyl Coated Polyester
- Coating: Poly Vinyl Chloride
- Construction: Woven
- Coating Distribution: 60% Front / 40% Back

FEATURES

- Sealing Properties: Dielectric, Thermal
- Mildew and UV Resistant

MECHANICAL PROPERTIES

- Grab Tensile: Meets ASTM D5034 Results: 696-741 Lbs.
- Strip Tensile: Meets ASTM D5035 Results: 356-530 Lbs.
- Tongue Tear: Meets ASTM D2261 Results: 84-111 Lbs.
- Adhesion: Meets ASTM D751 Results: 33 Lbs.
- Temperature: Meets ASTM D751
- Temperature Range: + 180°F Continuous to -41°F
- Meets RoHS
- This product can expose you to chemicals including di(2-ethylhexyl)phthalate (DEHP), which are known to the State of California to cause cancer and birth defects or other reproductive harm. For more information go to www.P65Warnings.ca.gov

BENEFITS

- Lightweight, tough, highly flexible
- Fast OEM & field service
- Easy to retrofit
- Fast and easy installation
- Proprietary bonding process allows cutting without fraying
- Easy to cut to length

Note: We reserve the right to make any engineering or material changes at any time to our products for enhancement, performance and quality.

Proper use of product is the sole responsibility of the user.

www.rhinosleeve.com

MADE IN USA





Тоидн

The Toughest Hose Protection Products on the Planet...Period!

RHINO BLUE VINYL WRAP™

Also available in Green, Yellow or Black



Meets RoHS

CHEMICAL RESISTANCE CHART							
Chemical	PVC	Chemical	PVC	Chemical	PVC		
Acetaldehyde	G	Diethyl Benzene	N	Methoxyethyl Oleate	N		
Acetamide	N	Diethyl Ether	F	Methyl Ethyl Ketone	N		
Acetic Acid, 5%	E	Diethyl Ketone	N	Methyl Isobutyl Ketone	N		
Acetic Acid, 50%	E	Diethyl Malonate	G	Methyl Propy1 Kelone	N		
Acetone	E	Dimethy1 Formamide	F	Methylene Chloride	N		
Aluminum Hydroxide	E	Ether	F	Nitric Acid. 50%	G		
Ammonia	E	Ethyl Acetate	F	Nitric Acid. 70%	F		
Ammonium Hydroxide	E	Ethyl Benzene	N	Nitrobenzene	N		
Ammonium Oxalate	E	Ethyl Benzoate	N	n-Octane	F		
n-Amyl Acetate	F	Ethyl Butyrate	N	Orange Oil	F		
Amyl Chloride	N	Ethyl Chloride, Liquid	N	Perchloric Acid	G		
Aniline	N	Ethyl Cyanoacetate	N	Perchloroethylene	N		
Benzaldehyde	N	Ethyl Lactate	F	Phenol, Crystals	F		
Benzene	N	Ethylene Chloride	N	Phosphoric Acid, 1-5%	E		
Benzoic Acid, Sat.	E	Ethylene Glycol	E	Phosphoric Acid, 85%	E		
Benzyl Acetate	F	Ethylene Oxide	F	Potassium Hydroxide	E		
Boric Acid	E	Fluorine	N	Propane Gas	E		
Bromine	G	Formic Acid, 50%	G	Propylene Glycol	F		
Bromobenzene	F	Formic Acid, 90-100%	F	Propylene Oxide	F		
n-Butyl Acetate	N	Fuel Oil	E	Resorcinol	F		
sec-Butyl Alcohol	G	Gasoline	G	Salicylaldehyde	F		
Butyric Acid	G	Glycerine	E	Sulfuric Acid. 1-6%	E		
Calcium Hypochlorile	G	n-Heptane	F	Sulfuric Acid. 20%	E		
Carbazole	N	Hexane	G	Sulfuric Acid. 60%	E		
Carbon Disulfide	N	Hydrochloric Acid. 1-5%	E	Sulfuric Acid. 98%	N		
Carbon Telrachloride	G	Hydrochloric Acid. 35%	G	Sulfur Dioxide, Liq.	F		
Chlorine	E	Hydrofluoric Acid, 4%	G	Sulfur Salts	N		
Chloroacelic Acid	F	Hydrofluoric Acid, 48%	G	Tartaric Acid	E		
Chloroform	N	Hydrogen	E	Telrahydrofuran	N		
Chromic Acid	E	Hydrogen Peroxide	E	Thionyl Chloride	N		
Citric Acid	G	Isopropyl Acetate	N	Toluene	F		
Cresol	N	Isopropyl Benzene	N	Trichloroelhane	N		
Cyclohexane	G	Kerosene	E	Trichloroelhylene	N		
Decalin	E	Lactic Acid, 3%	G	Turpentine	G		
o-Dichlorobenzene	G	Lactic Acid, 85%	G	Vinylidene Chloride	N		
p-Dichlorobenzene	N	Magnesium Salts	E	Xylene	N		
				Zinc Salts/Stearate	E		

This product can expose you to chemicals including di(2-ethylhexyl)phthalate (DEHP), which are known to the State of California to cause cancer and birth defects or other reproductive harm. For more information go to www.P65Warnings.ca.gov **Resistance**

Resistance E = Excellent

N = Not Recommended

This information is based on experience to date and is believed to be reliable.

F = Fair

G = Good

It is intended as a guide for use at your own discretion and risk. All indications refer to room temperature